


Resin Bound Stone Surfacing


Soft Surfaces Resin Bound Aggregate can be overlaid onto existing asphalt or concrete surfaces suitable for the traffic expected. The maximum tolerance of the base construction should not exceed 3mm under a 1m straight edge.

Any advise provided by Soft Surfaces Ltd is based on experience and is believed to be accurate at time of publication. No liability of responsibility of any kind is accepted in this respect by the company.

Permeable Car Park / Access Road (SUDS)




Fine Grit
Cast onto uncured surface



Soft Surfaces Resin Bound Surface Course
Trowelled to a smooth finish.
Typical Car Park depth using 6mm aggregate is 20mm



70mm (min) Open Binder Course Asphalt
AC20 open binder. Max 100/150 pen to BS EN 13108-1:2006 bituminous macadam



300-500mm MOT Type 3 Sub base
Well compacted non frost susceptible Type 3 granular sub base to SHW clause 805 or 4/40mm, 4/20mm graded crushed concrete aggregate to EN 12620 or locally available secondary or recycled aggregate complying to the above specification

Geotextile Membrane

Water House, 35 Water Lane, Wilmslow, Cheshire, SK9 5AR

Tel: 01625 445 760 Fax: 01625 525 619

info@softsurfaces.co.uk / www.softsurfaces.co.uk

